2016-11-15

Release of synthetic microplastic plastic fibres from domestic washing machines: Effects of fabric type and washing conditions

Napper, IE

<http://hdl.handle.net/10026.1/8163>

10.1016/j.marpolbul.2016.09.025

MARINE POLLUTION BULLETIN

Elsevier BV

All content in PEARL is protected by copyright law. Author manuscripts are made available in accordance with publisher policies. Please cite only the published version using the details provided on the item record or document. In the absence of an open licence (e.g. Creative Commons), permissions for further reuse of content should be sought from the publisher or author.

1

2 "This is a copy of the accepted paper as submitted for final publication. The final published
3 version can be found at:

4 <http://www.sciencedirect.com/science/article/pii/S0025326X16307639>

**Release of Synthetic Microplastic Plastic Fibres From Domestic Washing
Machines: Effects of Fabric Type and Washing Conditions**

Imogen E. Napper, Richard C. Thompson

*Marine Biology and Ecology Research Centre (MBERC), School of Marine Science
and Engineering, Plymouth University, Drake Circus, Plymouth, Devon, PL4 8AA*

Corresponding author: Imogen.Napper@Plymouth.ac.uk

Abstract

Washing clothes made from synthetic materials has been identified as a potentially important source of microscopic fibres to the environment. This study examined the release of fibres from polyester, polyester-cotton blend and acrylic fabrics. These fabrics were laundered under various conditions of temperature, detergent, and conditioner. Fibres from waste effluent were examined and the mass, abundance and fibre size compared between treatments. Average fibre size ranged between 11.9–17.7µm in diameter, and 5.0–7.8 mm in length. Polyester-cotton fabric consistently shed significantly fewer fibres than either polyester or acrylic. However, fibre release varied according to wash treatment with various complex interactions. We estimate over 728,000 fibres could be released from an average 6kg wash load of acrylic fabric. As fibres have been reported in effluent from sewage treatment plants, our data indicates fibres released by washing of clothing could be an important source of microplastics to aquatic habitats.

Keywords:

- Microplastic; Fabric; Waste Water Treatment; Ocean pollution; Litter; Debris

1. Introduction

Microplastics have accumulated in marine and freshwater environments, and in some locations outnumber larger items of debris (Browne et al., 2011; Thompson et al., 2004; Wagner et al., 2014). The sources of microplastic include the fragmentation of larger plastic items once they have entered the environment (secondary sources), and also the direct input of microplastic sized particles, such as microbeads used in cosmetics and pre-production pellets (Napper et al., 2015), or particles and fibres resulting from the wear of products while in use (primary sources). Microplastics can be ingested by a wide range of species both in marine (Anastasopoulou et al., 2013; Gall and Thompson, 2015; Lusher et al., 2013) and freshwater environments (Sanchez et al., 2014; Eerkes-Medrano et al., 2015). Laboratory studies indicate the potential for physical harm to biota from the result of ingestion (Wright et al., 2013). Ingestion could also facilitate the transfer of chemicals to organisms, however the relative importance of plastic debris as a vector in the transport for chemicals is not certain (Besseling et al., 2013; Rochman et al., 2013; Koelmans et al., 2013; Koelmans et al., 2014). Encounter rate, as well as polymer type and any associated chemicals (sorbed or additives) will influence the potential for effects in the environment (Teuten et al., 2007; Bakir et al., 2012; Koelmans et al., 2014; Bakir et al., 2014), therefore it is important to understand the relative abundance, as well as the sources of various types of microplastic.

Microplastic has been reported in a wide range of aquatic habitats, including beaches, surface waters, the water column and subtidal sediments (Lattin et al., 2004; Thompson et al., 2004), and there is evidence that the abundance is increasing (Thompson et al., 2004). They are also reported in some of the most remote environments, including the deep sea and the arctic, indicating their ubiquity and the need for further understanding about the potential environmental consequences (Obbard et al., 2014; Woodall et al., 2014).

Release of microplastic sized fibres as a result of washing of textiles has been widely reported as a potential source of microplastic (Browne et al., 2011; Dris et al., 2015; Essel et al., 2015; GESAMP, 2015; Wentworth and Stafford, 2016), however there has been little quantitative research on the relative importance of this source or on the factors that might influence such discharges. This is the focus of the research described here. In this context we consider microplastics as particles of plastic <5mm in their smallest dimension. While some fibres may be longer than 5mm they will usually have a diameter considerably less than 5mm. There is a lack of clarity on the formal definition for the lower size limit of microplastic and in environmental studies this has tended to relate more to the method of capture, e.g. mesh size of plankton nets used to sample water, or the method of identification such as spectroscopy. At present the smallest particles identified from the environment are around 20µm in their smallest dimension.

Textiles have the potential to release fibres into the environment, and one pathway is via laundering in washing machines. A range of fibres are used in the production of

76 textiles; these include natural fibres (such as cotton and wool), synthetic fibres (such
77 as nylon) and some are blends of natural and synthetic (such as polyester-cotton).
78 Synthetic fibres have been used to supplement cotton, wool, and linen in textiles for
79 more than 50 years, and fabrics such as polyester and acrylic are now widely used in
80 clothing, carpets, upholstery and other such materials. Washing of clothing has been
81 suggested as a potentially important source of microplastic fibres (Browne et al.,
82 2011).

83
84 Synthetic microplastic fibres are frequently reported in samples from sediments, the
85 water column and biota (Browne et al., 2011). Waste effluent from washing
86 machines, containing released fibres, will then travel via wastewater to sewage
87 treatment plants (Leslie et al., 2013; Dris et al., 2015). Due to the small size of the
88 fibres a considerable proportion could then pass through preliminary sewage
89 treatment screens (typically coarse, >6 mm, and fine screens, 1.5–6 mm) (Water
90 Environment Federation, 2003), and be released into aquatic environments. As
91 synthetic fibres are not readily decomposed by aerobic or anaerobic bacteria, any
92 that are intercepted in the sewage treatment plant will accumulate in sewage sludge,
93 and may subsequently be released back to the environment; for example if the
94 sludge is returned to the land or dumped at sea (Habib et al., 1998). Hence, there is
95 a considerable potential for fibres from synthetic textiles to accumulate in the
96 environment; for example, Gallagher et al (2016) found predominately fibres when
97 surveying the Solent estuarine complex (U.K.) for microplastic, similarly Dris et al
98 (2015), found considerable quantities of fibres in the River Seine. There is evidence
99 that some of this material can be transported as airborne particulates (Dris et al.,
100 2015); however it would appear that considerable quantities enter directly from

sewage treatment (Browne et al., 2011). To date, there has been limited research to establish the importance of clothing as a source of microplastic contamination to the environment.

A study by Browne et al (2011), sampled wastewater from domestic washing machines and suggested that a single garment could produce >1900 fibres per wash (Browne et al., 2011). To examine the role of the sewage system as a pathway to the environment, Browne extracted microplastic from effluent discharged by treatment plants, and also examined the accumulation of microplastic in sediments from sewage sludge disposal sites. On average, the effluents contained one particle of microplastic per litre, including polyester (67%) and acrylic (17%) and polyamide (16%); these proportions were similar to the relative proportions found on shorelines and disposal-sites (Browne et al., 2011). Similarly, a high number of plastic fibres were observed in the sediments near to a sewage outfall in Amsterdam (Leslie et al., 2013), and have been reported even 15 years after application in terrestrial soils that have received sewage sludge (Zubris and Richards, 2005). Unless the release of microplastics to waste water or sewage treatment practices change, the release of microplastic to the environment via sewage is likely to increase, as the human population grows. It is anticipated, for example, that reductions in emissions of microbeads via sewage will be reduced as a consequence of legislation to prohibit their use in cosmetics (Napper et al., 2015).

However, there are currently no peer reviewed publications that compare the quantity of fibres released from common fabrics due to laundering. In addition, the

potentially important influence of washing practices including temperature, the use of detergent and fabric conditioners have not been examined. Here we tested three different fabrics that are commonly used to make clothes; polyester, polyester-cotton blend, and acrylic. These fabrics were then laundered at two temperatures (30°C and 40°C), using various combinations of detergent and fabric conditioner. The fibres extracted from the waste effluent were examined to determine the typical size, and to establish any differences in the mass / abundance of fibres among treatments.

2. Method

Three synthetic fabric types were selected based on their prevalence in high-street retail stores close to Plymouth, UK. The chosen fabric types were all from jumpers (Fig. 2), with each being a different colour so they could be readily distinguished after fragmentation; 100% polyester (black), 100% acrylic (green) and 65% polyester / 35% cotton blend (blue). Four replicates of each garment were purchased, with each replicate sourced from a different retail outlet to provide a representative sample. The identity of each fabric type was confirmed by Fourier transform infra-red spectroscopy (FTIR), using a Hyperion 1000 microscope (Bruker) coupled to an IFS 66 spectrometer (Bruker). The spectra obtained were compared to a spectral database of synthetic polymers (Bruker I26933 Synthetic fibres ATRlibrary). As each garment varied in overall size, 20cm X 20cm squares were cut from the back panel of the garments and the edges hemmed by 0.5 cm using black and white cotton thread to deter the excess loss of fibres.

149 A Whirlpool WWDC6400 washing machine was used to launder the garment
150 samples. While it would be valuable to compare a range of washing machines this
151 was beyond the budget of the current research. This machine was selected as it is a
152 popular brand used for domestic laundry. The number of fibres released from the
153 wastewater outlet, as a result of laundering, was recorded. To achieve this, a nylon
154 CellMicroSieve™ (Fisher Scientific), with 25 µm pores, was attached to the end of
155 the drain hose. Once a cycle was complete, the CellMicroSieve™ was removed and
156 the fibres collected. Due to the potential build-up of detergent or conditioner on the
157 collected fibres, they were washed using 2L of water and filtered again over
158 Whatman N°4 filter papers, and then dried at 30°C to constant weight. Once dry, the
159 fibres were weighed by a Cubis® precision balance (Sartorius). The weight of fibres
160 were compared across four factors: Factor one, (fabric type, fixed factor, 3 levels:
161 100% polyester, 100% acrylic, and 65% polyester / 35% cotton blend); Factor two
162 wash temperature (fixed factor, 2 levels; 30°C and 40°C); Factor three, detergent (3
163 levels; detergent absent, 20ml bio-detergent present (contains enzymes), 20ml non-
164 bio detergent present); Factor four, conditioner (2 levels; 20ml conditioner absent or
165 present). Factors gave a total of 36 treatments (Fig.1).

166

167 In this study the main factors of interest were: fabric type, temperature, presence of
168 detergent and / or conditioner. The time of each wash and the rotations per minute
169 are clearly also factors of potential relevance but in order not to confound the
170 experimental design these were kept constant (Duration, 1 hour 15 minutes and
171 1400 rotations per minute (R.P.M)). Each treatment had four replicates.

172

173 Cross-contamination was minimized to <8 fibres per wash between washes, by
174 running the washing-machine at 30 °C, 1400 R.P.M for 45 minutes between washes
175 with no fabric present. Any initial spike in fibre loss from new clothes was reduced by
176 washing each fabric four times before recording any data. Care was taken to ensure
177 any potential sources of airborne contamination were minimised during the analysis
178 (Woodhall et al., 2015). The number of fibres released in the effluent from each
179 wash, N, was then estimated from the weight of captured fibres using the following
180 equations and assuming the fibres were of cylindrical shape:

181

182 i) $V_t = \frac{M_t}{D}$ ii) $V(\text{avg.fibre}) = \pi r^2 l$ iii) $N = \frac{V_t}{V(\text{avg.fibre})}$

183 where V_t is the total volume of fibres collected, M_t is the total mass of fibres collected,
184 D is the density, $V(\text{avg.fibre})$ is the mean volume of one fibre, N is number of fibres, l
185 is the height and r is the radius.

186 For each product: equation i) allowed calculation of the total volume of fibres
187 collected; equation ii) allowed calculation of the average volume of a fibre from each
188 garment; by dividing the total volume of fibres by the average volume of a single fibre,
189 equation iii) allowed calculation of the approximate number of fibres released in the
190 effluent from each wash.

191

192 Fibres were visualised by scanning electron microscopy (JEOL, 7001F); images
193 taken were used to measure the width of the fibres, and also to analyse their

topography. Images of the fibres were also taken by using LEICA M205C light microscope and analysed by Image J to measure their length (Rasband, 2015). For each fabric type, a mean size was calculated for length and width based on data from 10 individual fibres.

Using GMAV for windows, 4-Way Analysis of Variance (ANOVA) was used to establish any significant effects ($p < 0.05$) between treatments. Post-hoc SNK tests were then used to identify the location of any significant effects.

3.0 Results

Substantial numbers of microplastic fibres (smallest dimension, 5mm) were collected from jumpers made out of all three of the common man-made fabrics (polyester, acrylic and polyester-cotton blend) examined (Fig.2). These were discharged into wastewater from a generic cycle of a domestic washing machine. The fibres were confirmed to be the material type stated on the garment by Fourier transform infrared spectroscopy. Loss of fibres during the first 4 washes were recorded (Fig.3), but not included in the data analysis. Polyester showed a steady decrease in fibre loss overall: 1st wash (2.79 mg) to 5th (1.63 mg). Acrylic followed a similar pattern, but the fibre loss decreased more rapidly: 1st wash (2.63 mg) to 4th (0.99 mg). Polyester-Cotton Blend had the least variation, and showed little decrease between subsequent washes: 1st wash (0.45 mg) to 4th (0.30 mg). Since there was little

change in fibre release between the 4th and 5th wash data, data from the 5th wash was recorded for formal analysis.

While there was a consistent trend between fabric types, ANOVA revealed significant complex interactions between the 4 Factors (Table 1). Focussing on the type of fabric, polyester-cotton blend was consistently found to shed fewer fibres than both the other fabric types, regardless of the differing treatments. This trend was consistent for all 12 relevant interactive effects, and was significantly so for 9 out of these 12 interactions (Table 2a). However, the significance of this effect varied according to the treatment used, creating different interactions. There were some effects of temperature; For example, polyester was often found to release more fibres than acrylic at 40°C, when compared against 30°C (Table 2c).

There were also some significant effects of conditioner usage, where polyester-cotton blend consistently shed more fibres when conditioner was used. It was also shown that more fibres tended to be released with the addition of bio-detergent and conditioner. Detergent showed the least clear pattern; however, in some treatment combinations, having no detergent or using bio-detergent resulted in lower quantities of fibres being released. Polyester-cotton blend was also found to shed the least fibres when detergent was absent, and the most when non-bio detergent was used. Hence while there was a clear and fairly consistent trend between fabric types, the effects of temperature, detergent and conditioner were less consistent with some significant effects depending on the specific combinations of factors used.

239

240 The extracted fibres were visualised by scanning electron microscopy to examine the
241 differing shapes and surface topography. Polyester-Cotton blend fibres had a rough
242 texture, and were regularly observed as a fusion of 2 smaller fibres. Similarly, acrylic
243 fibres had an extremely coarse surface. Polyester fibres were smooth, without any
244 fracturing (Fig 2).

245

246 Acrylic fibres were on average 14.05 μm in diameter and 5.44 mm in length, giving
247 an average of 763,130 fibres per mg of dry fibres collected from the effluent.
248 Polyester fibres were on average 11.91 μm in diameter, but were longer at 7.79 mm,
249 resulting in around 475,998 fibres per mg. Polyester-cotton blend fibres were the
250 widest fibres being on average at 17.74 μm , but had the shortest length at 4.99 mm,
251 with an average 334,800 fibres per mg.

252

253 **4.0 Discussion**

254 The environmental consequences of microplastic contamination are not fully
255 understood. The quantity of microplastic in the environment is expected to increase
256 over the next few decades since even if new emissions of plastic debris halted the
257 fragmentation of legacy items that are already in the environment would be expected
258 to lead to an increase in abundance (Law and Thompson, 2014). There are concerns
259 about the potential for microplastics to have harmful effects if ingested and some
260 evidence of particle and chemical toxicity have come from relatively high dose
261 laboratory studies. Because of the persistent nature of plastic contamination, there is

growing awareness of the need to reduce inputs at source; this includes the direct release of microplastic sized particles including microbeads from cosmetics, and fibres from textiles.

Fibres from fabrics are known to be lost due to pilling. Pilling is defined as the entangling of the fabric surface during wearing or washing, resulting in formation of fibre balls (or pills) that stand proud on the surface of the fabric (Hussain et al., 2008). This occurs as a consequence of two processes: (i) fuzzing; the protrusion of fibres from the fabric surface, and (ii) pill formation; the persistence of formed neps (entangled masses of fibres) at the fabric surface (Naik and Lopez-Amo, 1982). The pill may be worn or pulled away from the fabric, as a consequence of mechanical action during either laundering or wear (Yates, 2002).

Most fabrics pill to some extent and this has always been a concern in the industry as it spoils surface appearance and comfort, reduces the fabric's strength and diminishes its serviceability (Hussain et al., 2008; Chiweshe and Crews, 2000). This problem has become more prominent with the widespread use of synthetic fibres, such as polyester and acrylic, due to their higher tensile strength (Cooke, 1985). These synthetic fibres are widely used because of their low cost and versatile use. Laundry methods have been recognised as being important to minimise the pilling tendency (Cooke, 1985).

The rate or extent to which the pilling stages occur is determined by the physical properties of the fibres which comprise the fabric (Gintis and Mead, 1959). From the

fabrics tested here, polyester-cotton blend consistently shed significantly fewer fibres than either of the other fabric types which were entirely synthetic. Polyester is often added to cotton fabric to reduce cost, whilst also increasing tenacity and resilience. This is because cotton fibres have a lower tenacity, and as the pills are formed, the anchor fibres are easily broken; if the tenacity of the fabric is increased with added polyester, the pill break-off rate is lower, resulting in less fibres being released (McCloskey and Jump, 2005).

Polyester fibres have many desirable properties, including good resistance to strain and deformation (Pastore and Kiekens, 2000). 100% polyester fabrics are renowned for pilling, but because of their high tenacity, the anchor fibres rarely break releasing the pills (Nunn, 1979). Previous research has even reported that as the polyester fibre content in a polyester-cotton blend fabric increases, the pilling gets worse (Gintis and Mead, 1959; Ruppenicker and Kullman, 1981). On the contrary our research found that polyester fabrics yielded significantly more fibres than polyester-cotton blend. It has previously been suggested that pilling of polyester can be controlled by the modification of the polyester properties, where a greater fibre release can improve polyester fabrics surface appearance (Doustaneh et al., 2013). Weakening the fibres (reduced ultimate bending stiffness), leads to more rapid break-off of pills due to fibre fatigue, leading to greater fibre release while at the same time improving the fabrics topography and surface appearance (Doustaneh et al., 2013). Hence from an aesthetic perspective, there may be benefits to the release of pills from garments during washing. However, this can also create a trade-off between garment appearance, and fibre release. More research would be needed to

309 establish how release rates vary over the lifetime of a garment in service in order to
310 fully establish the temporal dynamics of fibre emissions.

311

312 During the laundering of clothes, detergent and fabric conditioner are often used in
313 combination. Synthetic detergents remove the oils and waxes that serve as
314 lubricants in natural fibres, making a garment clean but harsh, scratchy, and
315 uncomfortable to wear (Egan, 1978). Fabric softeners are used to counteract these
316 effects. In addition, the use of fabric conditioners can reduce the build-up of static
317 electricity, which can make the fabric objectionable to the wearer. Fabric softeners
318 act as antistatic agents by enabling synthetic fibres to retain sufficient moisture to
319 dissipate static charges (Ward, 1957).

320

321 Fabric conditioners may also increase pilling, and this is especially the case for
322 synthetic fibres (Smith and Block, 1982). Work by Chiweshe and Crews (2000),
323 showed that use of fabric conditioner on all cotton-containing fabrics resulted in
324 increased pilling and/or an increase in the size of pills, as well as increased breaking
325 strength losses in polyester woven fabric. Hence, it might be expected that the
326 presence of conditioner could increase the release of fibres. This was observed in
327 some of the treatment combinations here, but there was no clear trend relating to the
328 presence of conditioner.

329

330 Detergent use presented the least clear pattern for fibre release when compared
331 against the other factors. However, it was found that having no detergent or bio-

detergent in a wash cycle occasionally resulted in the fewer fibres being released. Previous research has also shown that when polyester-cotton blend fabric has been laundered with a bio-detergent, it exhibited less piling than when laundered using a non-bio (Chiweshe and Crews, 2000). Our research produced some similar results, where polyester-cotton blend was also found to shed fewer fibres when detergent was absent, and the most when non-bio detergent was used.

Using the results from this experiment, the number of fibres potentially released into washing machine waste water per wash was estimated. This was achieved by examining the average fibre size, the various Factors tested and assuming a typical washing load of 6kg. Based on this, a washing load (6kg) of polyester-cotton blend was estimated to release 137,951 fibres; polyester to potentially release 496,030 and Acrylic 728,789. The large number of fibres released when clothing is laundered is therefore likely to represent a substantial contributor to microplastic contamination in the environment. Our estimates are similar to research by Browne et al (2011), where it was suggested that a single garment could produce >1900 fibres per wash (Browne et al., 2011).

Wastewater Treatment Plants (WWTPs) play a critical role in the fate and transport of microfibres into the environment. In countries with sewage infrastructure, the effluent from washing machines is discharged into the local sewer system. This is then treated by a WWTP and discharged as treated effluent, which is released into the aquatic environments. Effluent discharge often contains suspended solids, such as microfibres, which are not removed during the treatment processes. In

Amsterdam, Leslie et al. (2013) found concentrations from WWTP effluent ranged from 9 particles/L (min.) to 91 particles/L (max.) with a mean and median of 52 particles/L. However, a study by Murphy et al., (2016) compared the influent and effluent from a WWTP. The influent contained on average 15.70 (± 5.23) microplastic/L, and was found to be reduced to 0.25 (± 0.04) microplastic/L in the final effluent, a decrease of 98.41%. However, Mintenig et al. (2014) calculate emissions of between 93 and 8.2 billion microplastics and synthetic fibres being discharged from wastewater treatment plants in Germany (Essel et al., 2015). However, even a small amount of microplastic being released per litre can result in substantial amounts of microplastics entering the environment due to the large volumes being treated. It has been predicted that a WWTP plant in the United Kingdom could release up to 65 million microplastics into the receiving water every day (Murphy et al., 2016).

Even if WWTPs are completely effective in the removal of microfibrils, the extracted plastic particles may still enter the environment if the resultant sewage sludge, a by-product of the wastewater treatment process is returned to the land, for example as a fertilizer (Habib et al., 1998; Zubris and Richards, 2005). Microfibrils in sewage sludge may subsequently persist in the terrestrial environment, or be transported to aquatic environments via runoff. The potential for sewage sludge to transfer microplastic into the marine environment was shown in a preliminary study by Habib et al. (1998), where sediments were collected from a bay downstream of a sewage treatment plant. It was found that the sediment contained numerous synthetic fibres and as distance from the sewage treatment plant increased the size and number of fibres decreased. This effect was also observed by McCormick et al (2014), where a

381 higher concentration of microplastic (17.93 m^3) was recorded downstream of a
382 WWTP, compared to upstream (1.91 m^3) (McCormick et al., 2014).

383

384 Clothing design, including the type of fabric used, clearly has considerable potential
385 to influence fibre release; for example our research, found that a fabric made from a
386 synthetic-natural combination released around 80% fewer fibres than acrylic.
387 Further work to better understand how fabric design and textile choice influence fibre
388 release should therefore be undertaken. Important direction for future research
389 include comparing release between different types of washing machine and using a
390 variety of wash duration and spin speed together with an assessment of the
391 temporal dynamics of fibre release throughout a products life time.

392

393 From the perspective of sustainability and environmental contamination, criteria for
394 synthetic garment manufacture should consider: 1) performance in service, giving a
395 long lasting product that remains attractive during usage; 2) minimal release of non-
396 degradable synthetic fibres and 3) a product that is compatible with end of life
397 recycling. Such factors need to be taken into account throughout the design and
398 manufacturing stages; for example including consideration of fibre properties
399 (composition, length), spinning method and the weaving/knitting process. Inadequate
400 consideration of potential environmental impacts at the product design stage has led
401 to considerable negative publicity and restrictive legislation relating to emissions of
402 plastic microbeads from cosmetics (Napper et al., 2015); clearly illustrating the
403 benefit of a precautionary approach. As well as considering direct environmental
404 impacts of manufacture, product use and disposal there is a growing realisation of

405 the need for a more circular approach to material usage in order to maximise long
406 term resource sustainability and waste minimisation via a circular economy
407 (European Commission, 2012; World Economic Forum, 2016). The Plastic Soup
408 Foundation and MERMAIDS Life+ project are currently promoting development of
409 innovative solutions to minimise the release of plastic fibres from garments. Filters
410 for washing machines are also being developed, (Mermaids Organisation, 2015).
411 These are made of a stainless steel mesh with hole diameters of 0.0625 inches, to
412 collect fibres (Environmental Enhancements, 2016). For this measure to be
413 successful it will be essential to ensure the filters are not subsequently disposed of
414 via household liquid waste. However, from a material usage and efficacy perspective
415 minimising fibre release at the design stage should be regarded as the most effective
416 priority in a management hierarchy.

417

418 In conclusion, this work examined the release of textile fibres from three fabrics that
419 are commonly used to make clothing (polyester, polyester-cotton blend and acrylic).
420 The results show that laundering 6kg of synthetic materials could release between
421 137,951 – 728,789 fibres per wash. Our results indicate significant effects of wash
422 conditions, but no clear picture based on the two detergents and one conditioner
423 used. Hence, further work to examine in more detail differing washing machines and
424 wash treatments involving wash duration and spin speed as well as temperature,
425 detergent and conditioner may be worthwhile. This could help establish whether
426 specific wash conditions could be used to help minimise fibre release. Temporal
427 dynamics of release over the life time of a product should also be examined and as
428 this could help extend garment life while at the same time reducing fibre emissions.

429

Figures

430

431

432

433

435

436 **Figure 1.** *Experimental design showing Factors used for each fabric type (acrylic,*
437 *polyester, polyester-cotton blend).*

438

439

Figure 2. Images to show the original garments (each representing a different fabric), and a scanning electron microscopy image (SEM) of a typical fibre from each fabric (the scale bar is consistent for all images - 2500 X magnification). Key details are included below about the mean dimensions of fibres released during laundering, and estimated quantity released from the fabric during each wash (assuming a typical washing load of 6kg).

Figure 3. Fibre loss from three fabrics (acrylic, polyester & polyester-cotton blend), over the first 5 washes. Data from the 5th wash was used in the analysis (n = 4, $\pm$ SD).

Tables

SOURCE	Df	MS	F	P
Fabric	2	5.36	83.18	0.00
Temp	1	0.10	1.54	0.22
Cond	1	0.37	5.67	0.02
Deter	2	0.52	8.07	0.00
FabricXTemp	2	0.02	0.33	0.72
FabricXCond	2	0.12	1.88	0.16
FabricXDeter	4	0.20	3.13	0.02
TempXCond	1	0.15	2.28	0.13
TempXDeter	2	0.13	2.09	0.13
CondXDeter	2	0.58	9.00	0.00
FabricXTempXCond	2	0.06	0.86	0.43
FabricXTempXDeter	4	0.06	1.00	0.41
FabricXCondXDeter	4	0.33	5.05	0.00
TempXCondXDeter	2	0.64	9.91	0.00
FabricXTempXCondXDeter	4	0.38	5.95	0.00
Residual	108	0.06		
Total	143			

Table 1. Analysis of variance (ANOVA) for factors affecting release of fibres as a consequence of various laundering treatments (n=4; **bold** = $p = <0.05$). Key: Temp (temperature), Deter (Detergent), Cond (Conditioner).

a) FABRIC				b) DETERGENT			
Factors		Order		Factors		Order	
30	C-	No Powder	Blend<*Acr<*PE	Acr	30	C-	bio-NB-A
30	C-	Bio	Blend<*Acr-PE	Acr	30	C+	A-NB-bio
30	C-	Non Bio	Blend-PE-Acr	Acr	40	C-	A-NB-bio
30	C+	No Powder	Blend<*PE-Acr	Acr	40	C+	bio-NB<*A
30	C+	Bio	Blend<*PE-Acr	Blend	30	C-	bio-A-NB
30	C+	Non Bio	Blend<*Acr-PE	Blend	30	C+	A-bio-NB
40	C-	No Powder	Blend<*Acr<*PE	Blend	40	C-	A-bio<*NB
40	C-	Bio	Blend<*PE<*Acr	Blend	40	C+	A-NB-bio
40	C-	Non Bio	Blend-Acr<*PE	PE	30	C-	bio-NB<*A
40	C+	No Powder	Blend<*PE<*Acr	PE	30	C+	A-bio-NB
40	C+	Bio	Blend-Acr<*PE	PE	40	C-	bio<*A<*NB
40	C+	Non Bio	Blend<*Acr-PE	PE	40	C+	A-NB-bio
c) TEMPERATURE				d) CONDITIONER			
Factors		Order		Factors		Order	
Acr	C-	No Powder	40-30	Acr	30	No Powder	C-A
Acr	C-	Bio	30<*40	Acr	30	Bio	A<*C
Acr	C-	Non Bio	30-40	Acr	30	Non Bio	A-C
Acr	C+	No Powder	30-40	Acr	40	No Powder	A<*C
Acr	C+	Bio	40<*30	Acr	40	Bio	C-A
Acr	C+	Non Bio	40-30	Acr	40	Non Bio	C-A
Blend	C-	No Powder	40-30	Blend	30	No Powder	A-C
Blend	C-	Bio	40-30	Blend	30	Bio	A-C
Blend	C-	Non Bio	30<*40	Blend	30	Non Bio	A-C
Blend	C+	No Powder	30-40	Blend	40	No Powder	A-C
Blend	C+	Bio	30-40	Blend	40	Bio	A<*C
Blend	C+	Non Bio	30-40	Blend	40	Non Bio	C<*A
PE	C-	No Powder	40-30	PE	30	No Powder	C<*A
PE	C-	Bio	40-30	PE	30	Bio	A-C
PE	C-	Non Bio	30<*40	PE	30	Non Bio	A<C
PE	C+	No Powder	40-30	PE	40	No Powder	C-A
PE	C+	Bio	40-30	PE	40	Bio	A<*C
PE	C+	Non Bio	40-30	PE	40	Non Bio	C<*A

467

468 **Table 2.** Outcomes of SNK tests for specific combinations of the factors: a) fabric, b)
469 detergent, c) temperature, d) conditioner. For each combination the relative
470 number of fibres released is indicated by the sequence shown with
471 permutation leading to the greatest release of fibres being shown to the right.
472 Specific variables tested against three different fabric types (acrylic,

polyester & polyester-cotton blend), and the subsequent fibre extract from
*laundering (n=4; * = p (<0.05)).* Key: PE (polyester), Blend (polyester-cotton
blend), Acr (acrylic), A (conditioner/detergent absent), C (conditioner
present), NB (non-bio detergent), bio (bio detergent).

495 Acknowledgements

496

497 The authors would like to thank Andrew Tonkin, Richard Ticehurst and the MBERC
498 technicians for their help throughout the project.

499

500 References

501

502 Anastasopoulou, A., Mytilineou, C., Smith, C.J., Papadopoulou, K.N., 2013. Plastic
503 debris ingested by deep-water fish of the Ionian Sea (Eastern Mediterranean),
504 Deep Sea Research Part I: Oceanographic Research Papers.
505 doi:10.1016/j.dsr.2012.12.008

506 Bakir, A., Rowland, S. J., Thompson, R. C. 2012. Competitive sorption of persistent
507 organic pollutants onto microplastics in the marine environment. Marine
508 Pollution Bulletin 64, 2782-2789

509 Bakir, A., Rowland, S. J., Thompson, R. C. 2014. Enhanced desorption of persistent
510 organic pollutants from microplastics under simulated physiological conditions.
511 Environmental Pollution 185, 16-23

512 Besseling, E., Wegner, A., Foekema, E.M., Van Den Heuvel-Greve, M.J., Koelmans,
513 A.A., 2013. Effects of microplastic on fitness and PCB bioaccumulation by the
514 lugworm *Arenicola marina* (L.). Environ. Sci. Technol. 47, 593–600.
515 doi:10.1021/es302763x

516 Browne, M.A., Crump, P., Niven, S.J., Teuten, E., Tonkin, A., Galloway, T.,
517 Thompson, R., 2011. Accumulation of Microplastic on Shorelines Worldwide:

518 Sources and Sinks. Environ. Sci. Technol. 45, 9175–9179.
519 doi:10.1021/es201811s

520 Browne, M.A., Dissanayake, A., Galloway, T.S., Lowe, D., Thompson, R., 2008.
521 Ingested microscopic plastic translocates to the circulatory system of the mussel,
522 *Mytilus edulis* (L). Environ. Sci. Technol. 42, 5026–5031.

523 Cooke, W.D., 1985. Pilling Attrition and Fatigue. Text. Res. J. 55, 409–414.
524 doi:10.1177/004051758505500705

525 Doustaneh, A.H., Mahmoudian, S., Mohammadian, M., Jahangir, A., 2013. The
526 Effects of Weave Structure and Yarn Fiber Specification on Pilling of Woven
527 Fabrics. World Appl. Sci. J. 24, 503–506.

528 Dris, R., Gasperi, J., Rocher, V., Saad, M., Renault, N., Tassin, B. 2015. Microplastic
529 contamination in an urban area: a case study in Greater Paris. Environmental
530 Chemistry 12, 592-599.

531 Egan, R.R., 1978. Cationic surface active agents as fabric softeners. J. Am. Oil
532 Chem. Soc. 55, 118–121. doi:10.1007/BF02673399

533 Environmental Enhancements, 2016. About the Lint LUV-R Filter [WWW Document].
534 URL <http://www.environmentalenhancements.com/Lint-LUV-R-about-luv-r.html>

535 Eerkes-Medrano, D., Thompson, R. C. , Aldridge, D. C. 2015. Microplastics in
536 freshwater systems: A review of the emerging threats, identification of
537 knowledge gaps and prioritisation of research needs. Water Research 75, 63-82.

538 Essel, R., Engel, L., Carus, M., Ahrens, R. H. 2015. Sources of microplastics
539 relevant to marine protection in Germany, pp. 48.

540 Gall, S.C., Thompson, R.C., 2015. The impact of debris on marine life. *Mar. Pollut.*
541 *Bull.* 92, 170–9. doi:10.1016/j.marpolbul.2014.12.041

542 GESAMP. 2015. Sources, fate and effects of microplastics in the marine
543 environment: a global assessment. In GESAMP No. 90 (ed. P. J. Kershaw), pp.
544 96: IMO/FAO/UNESCO-IOC/UNIDO/WMO/IAEA/UN/UNEP/UNDP Joint Group
545 of Experts on the Scientific Aspects of Marine Environmental Protection.

546 Gintis, D., Mead, E.J., 1959. The Mechanism of Pilling. *Text. Res. J.* 29, 578–585.
547 doi:10.1177/004051755902900709

548 Habib, D., Locke, D.C., Cannone, L.J., 1998. Synthetic fibers as indicators of
549 municipal sewage sludge, sludge products and swage treatment plant effluents.
550 *Water Air Soil Pollut.* 103, 1–8.

551 Hussain, T., Ahmed, S., Qayum, A., 2008. Effect of different softeners and
552 sanforising treatment on pilling performance of polyester/viscose blended fabrics.
553 *Color. Technol.* 124, 375–378. doi:10.1111/j.1478-4408.2008.00166.x

554 Koelmans, A. A., Besseling, E., Wegner, A., Foekema, E. M. 2013. Plastic as a
555 carrier of POPs to aquatic organisms: A model analysis. *Environmental Science*
556 *and Technology* 47, 7812-7820.

557 Koelmans, A. A., Gouin, T., Thompson, R. C., Wallace, N., Arthur, C. 2014. Plastics
558 in the marine environment. *Environmental Toxicology and Chemistry* 33, 5-10.

559 Law, K. L., Thompson, R. C. 2014 Microplastics in the seas. *Science* 345, 144-145.

560 Lattin, G.L., Moore, C.J., Zellers, A.F., Moore, S.L., Weisberg, S.B., 2004. A
561 comparison of neustonic plastic and zooplankton at different depths near the
562 southern California shore. *Mar. Pollut. Bull.* 49, 291–294.

563 doi:10.1016/j.marpolbul.2004.01.020

564 Leslie, H.A., Van Velzen, M.J.M., Vethaak, A.D., 2013. Microplastic survey of the
565 Dutch environment Novel data set of microplastics in North Sea sediments,
566 treated wastewater effluents and marine biota, IVM Institute for Environmental
567 Studies.

568 Lusher, A.L., McHugh, M., Thompson, R.C., 2013. Occurrence of microplastics in the
569 gastrointestinal tract of pelagic and demersal fish from the English Channel 67,
570 94–99. doi:10.1016/j.marpolbul.2012.11.028

571 McCloskey, S.G., Jump, J.M., 2005. Bio-Polishing of Polyester and Polyester/Cotton
572 Fabric. Text. Res. J. 75, 480–484. doi:10.1177/0040517505053846

573 McCormick, A., Hoellein, T.J., Mason, S.A., Schluep, J., Kelly, J.J., 2014.
574 Microplastic is an Abundant and Distinct Microbial Habitat in an Urban River.
575 Environ. Sci. Technol. 48, 11863–11871. doi:10.1021/es503610r

576 Mermaids Organisation, 2015. Newsletter 2 Life+ project Mermaids [WWW
577 Document]. URL <http://life-mermaids.eu/en/newsletter-2-life-mermaids/>

578 Mintenig, S.; Int-Veen, I.; Löder, M., G. Gerdt., 2014. Mikroplastik in ausgewählten
579 Kläranlagen des Oldenburgisch- Ostfriesischen Wasserverbandes (OOWV) in
580 Niedersachsen. Abschlussbericht des Alfred-Wegener-Instituts (AWI) im Auftrag
581 des Oldenburgisch-Ostfriesischen Wasserverbandes (OOWV) und des
582 Niedersächsischen Landesbetriebs für Wasserwirtschaft, Küsten- und
583 Naturschutz (NLWKN)

584

585 Murphy, F., Ewins, C., Carbonnier, F., Quinn, B., 2016. Wastewater Treatment
 586 Works (WwTW) as a Source of Microplastics in the Aquatic Environment.
 587 Environ. Sci. Technol. 50, 5800–5808. doi:10.1021/acs.est.5b05416

588 Naik, A., Lopez-Amo, F., 1982. Pilling Propensity of Blended Textiles. Melliand
 589 Textilbericht 6.

590 Napper, I.E., Bakir, A., Rowland, S.J., Thompson, R.C., 2015. Characterisation,
 591 quantity and sorptive properties of microplastics extracted from cosmetics. Mar.
 592 Pollut. Bull. 99, 178–185. doi:10.1016/j.marpolbul.2015.07.029

593 Nunn, D.M. (Ed.), 1979. The Dyeing of Synthetic Polymer and Acetate Fibres. The
 594 Dyers Company Publications Trust, West Yorkshire.

595 Obbard, R.W., Sadri, S., Wong, Y.Q., Khitun, A.A., Baker, I., Thompson, R.C., 2014.
 596 Global warming releases microplastic legacy frozen in Arctic Sea ice. Earth's
 597 Futur. 2, 315–320. doi:10.1002/2014EF000240

598 Rasband, W., 2015. ImageJ. U. S. Natl. Institutes Heal. Bethesda, Maryland, USA,
 599 //imagej.nih.gov/ij/.

600 Rochman, C.M., Hoh, E., Kurobe, T., Teh, S.J., 2013. Ingested plastic transfers
 601 hazardous chemicals to fish and induces hepatic stress. Sci. Rep. 3, 3263.
 602 doi:10.1038/srep03263

603 Ruppenicker, G.F., Kullman, R.M.H., 1981. Properties of Yarns and Fabrics
 604 Produced from High-Cotton-Content Blends with Polyester Fibers. Text. Res. J.
 605 51, 590–596. doi:10.1177/004051758105100906

606 Sanchez, W., Bender, C., Porcher, J.M., 2014. Wild gudgeons (*Gobio gobio*) from

607 French rivers are contaminated by microplastics: Preliminary study and first
608 evidence 128, 98–100. doi:10.1016/j.envres.2013.11.004

609 Smith, B., Block, I., 1982. Textiles in Perspective. Prentice Hall, New Jersey, U.S.A.

610 Teuten, E.L., Rowland, S.J., Galloway, T.S., Thompson, R.C., 2007. Potential for
611 Plastics to Transport Hydrophobic Contaminants. Environ. Sci. Technol. 41,
612 7759–7764.

613 Thompson, R.C., Olsen, Y., Mitchell, R.P., Davis, A., Rowland, S.J., John, A.W.G.,
614 McGonigle, D., Russell, A.E., 2004. Lost at sea: where is all the plastic? Science
615 304, 838. doi:10.1126/science.1094559

616 Wagner, M., Scherer, C., Alvarez-Muñoz, D., Brennholt, N., Bourrain, X., Buchinger,
617 S., Fries, E., Grosbois, C., Klasmeier, J., Marti, T., Rodriguez-Mozaz, S.,
618 Urbatzka, R., Vethaak, A.D., Winther-Nielsen, M., Reifferscheid, G., 2014.
619 Microplastics in freshwater ecosystems: what we know and what we need to
620 know. Environ. Sci. Eur. 26, 12Wagner, Martin Scherer, Christian Alvarez–
621 Muñoz,. doi:10.1186/s12302-014-0012-7

622 Ward, H., 1957. Textile Softeners for Home Laundering. J. Home Econ. 49.

623 Wentworth, J., Stafford, C., 2016. Marine Microplastic Pollution, POSTNOTE (528),
624 Houses of Parliament, UK. URL
625 [http://researchbriefings.parliament.uk/ResearchBriefing/Summary/POST-PN-](http://researchbriefings.parliament.uk/ResearchBriefing/Summary/POST-PN-0528?utm_source=website&utm_medium=website&utm_campaign=PN528)
626 [0528?utm_source=website&utm_medium=website&utm_campaign=PN528](http://researchbriefings.parliament.uk/ResearchBriefing/Summary/POST-PN-0528?utm_source=website&utm_medium=website&utm_campaign=PN528)

627 Woodall, L. C., Gwinnett, C., Packer, M., Thompson, R. C., Robinson, L. F.,
628 Paterson, G. L. J. 2015. Using a forensic science approach to minimize
629 environmental contamination and to identify microfibres in marine sediments.

630 Marine Pollution Bulletin 95, 40-46.

631 Woodall, L.C., Sanchez-Vidal, A., Canals, M., Paterson, G.L.J., Coppock, R., Sleight,
632 V., Calafat, A., Rogers, A.D., Narayanaswamy, B.E., Thompson, R.C., 2014.
633 The deep sea is a major sink for microplastic debris. R. Soc. Open Sci. 1,
634 140317–140317. doi:10.1098/rsos.140317

635 Wright, S.L., Thompson, R.C., Galloway, T.S., 2013. The physical impacts of
636 microplastics on marine organisms: A review. Environ. Pollut. 178, 483–492.
637 doi:10.1016/j.envpol.2013.02.031

638 Yates, M., 2002. Fabrics: A Guide for Interior Designers and Architects. W.W. Norton,
639 New York.

640 Zubris, K.A. V, Richards, B.K., 2005. Synthetic fibers as an indicator of land
641 application of sludge. Environ. Pollut. 138, 201–11.
642 doi:10.1016/j.envpol.2005.04.013

643